



versalis

Catalogo Prodotti

Stirenici-ABS



Stirenici

ABS

Sinkral

Nome prodotto	Indice di fluidità 220°C - 10 kg g/10'	Temperatura di rammollimento Vicat B 50 N - 120°C/h °C	Izod, con intaglio 23°C - 4 mm kJ/m2	Tipo	Applicazioni Principali
B 432/E	4	104	18	general purpose for extrusion	industrial sheets, furnishing profiles
B 532/E	5	104	20	improved impact for extrusion	industrial sheets, furnishing profiles
B 732/E	4,5	104	28	outstanding thermal - impact balance	industrial sheets, furnishing profiles
B4 MILANO	4	104	18	smooth finishing very low gels content	industrial sheets, furnishing profiles
B4 VENEZIA	6	104	15	glossy finishing and high modulus	industrial sheets, furnishing profiles
C 333/M2	5	103	14	medium gloss for transport sector	dashboards, automotive interiors
C 442	6	108	17	medium heat	automotive interiors, rear view mirrors
E 332	10	104	15	general purpose for injection and alloys	automotive interiors, alloys
F 332	14	102	14	medium flow, glossy for injection	small appliances, electrical components
L 322	26	96	13	easy flow, glossy for injection	household appliances, toys
M4 MODENA	8	101	9,5	super matt finishing - reduced roughness	industrial sheets, furnishing profiles



versalis

Stirenici-ABS